WASHINGTON PENN
An AUDIA® Company

washingtonpenn.com

Processing Guidelines

PPH3GF4.5 - (Any Color)

Pressure

Injection	600 - 1600 psi	41 - 97 Bar
Holding	150 - 900 psi	10 - 48 Bar
Back	075 - 125 psi	5 - 9 Bar

Injection Speed

	1.0 - 2.5 in/s	25 - 63 mm/s

Temperatures

• Barrel Zone 1	420 - 450 °F	216 - 232°C
• Barrel Zone 2	420 - 450 °F	216 - 232°C
• Barrel Zone 3	430 - 460 °F	221 - 238°C
• Barrel Zone 4	440 - 470 °F	227 - 243°C
• Nozzle	440 - 470 °F	227 - 243°C
• Hot Runner	440 - 470 °F	227 - 243°C
• Mold	60 - 160 °F	16 - 71°C
• Hydraulic Oil Temperature	110 - 125 °F	43 - 52 °C

Material Drying is typically not required but for some thin walled parts drying may be required. If needed dry at 160 - 190 °F (71 - 88 °C) for 1-2 hours.

Machine/Shot Information

Shot Capacity vs. Barrel Capacity	2.5 to 4.0	
Cushion	1/8" to 1/4"	3 mm - 6 mm
Screw Decompression	0.10 in - 0.25 in	2.5 mm - 6.3 mm

Clamp Tonnage should be 2.5 to 4.0 Tons per square inch of projected part area.

If you have any questions or require further processing information, please e-mail the Technical Service Group at wp.techservices@audia.com

These process conditions are typical processing parameters for injection molding. Use of these operating conditions, however, does not guarantee desired performance for all applications because of potential variability in a variety of factors including, but not limited to, gating, molding equipment, injection mold screw design, dispersion equipment, tooling, tool steel type, cooling capability, and part geometry. Washington Penn Plastic Co., Inc. makes no representations or warranties concerning product performance in any application.